

# Fasson® High Gloss Paper/S2090/BG40 Wht (Imp.)

Spec# / AW0153

Last Modified: 18-Mar-2010

#### **Facestock**

A white, one side gloss finished cast coated paper.

Basis Weight 80 g/m² TAPPI T410 Caliper 88 µm TAPPI T411

#### **Adhesive**

S2090 is a general purpose permanent, emulsion acrylic adhesive.

# **Typical Performance Data**

Initial Tack 13.5 or tear FTM 9 glass

N/25mm

Peel Adhes. 90° 10.5 or tear FTM 2 st.st.

N/25mm

Min. appl. temp. 5°C

Service temp. -20 °C to 80 °C subject to facestock

limitations

### **Food Industry Labels**

The adhesive complies with FDA regulations (section 175.105) for indirect food contact.

#### Liner

BG40 is a high density glassine paper featuring high internal strength, toughness and tear resistance as well as high transparency.

#### Laminate

Total Caliper 150 µm +/- 10%

## **Applications and Uses**

This product is suitable for a wide range of promotional and industrial labels whereby brilliant multicolour print quality and attractive gloss appearance are required.

Typical applications include labels for use in the cosmetic, pharmaceutical, food industry, chemical products and promotional labels.

# **Printing / Converting**

This glossy, cast coated quality is specially suited to provide top printing quality in all usual printing techniques, whether single or multi-colour, line or process colour printing.

NOTE: For superior solid print quality, we recommend to use High Gloss White products. High internal strength of the glassine liner provides excellent support for die cutting both rotary and flat bed.

### **Shelf Life**

One year when stored at 22 °C and 50% R.H.

#### Statement of Practical Use

As with all pressure sensitive materials, this product should be tested thoroughly under end-use conditions to ensure it meets the requirements of the specific application.



Avery Dennison (Thailand) Ltd. Avery Dennison Singapore Pte. Ltd. P.T. Avery Dennison Indonesia Avery Dennison Materials Sdn. Bhd. ADC Philippines Inc.

Avery Dennison (Vietnam) Limited

Tel: +66 2 750 2070 Fax: +66 2 750 2071
Tel: +65 6349 0333 Fax: +65 6278 2455
Tel: +62 21 893 6033 Fax: +62 21 893 6031
Tel: +60 3 8925 0901 Fax: +60 3 8925 0903
Tel: +63 2 916 6816 Fax: +63 2 682 8243
Tel: +84 8 3816 4639 Fax: +84 8 3816 4638

## Warranty

Information concerning Products are based upon tests believed to be reliable but do not represent a guarantee or warranty. Products are provided on the basis that any Purchaser has independently determined the suitability of the Products and Purchaser's purposes. The Company warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year of delivery (but not afterwards), upon notification thereof within seven (7) days of such appearance and substantiation that the Products have been stored and applied in accordance with the Company standards, the Company shall within a reasonable period correct such defects by providing a suitable replacement without charge at the Company's plant or at the location of the Products (at the Company's election) provided however, if the Company in its sole discretion determines that replacement is not commercially practical, the Company may issue a credit in favour of the Purchaser in an amount not to exceed the purchase price actually paid for the Products. Any implied warranty of merchantability fitness for particular purpose or other warranty of quality, whether express or implied by law, is hereby excluded to the extend permitted by law. In no event shall the Company be liable for any incidental, indirect or consequential damages including, but not limited to, loss of profit, loss of use or loss of capital. The remedies of the Purchaser set forth herein are exclusive, and the total potential liability of the Company arising out of any contract of or from the manufacture, sale, delivery, resale, installation or use of any products shall not exceed the purchase price

of the products upon which liability is based.