

Product Component Guide

ASEAN 2022





Contents

How to Use this Guide 3

Important Information 4

Facestock

Facestock contents 7

Quick Compare Guide 10

Prime Paper 12

Prime Film 15

VI Paper 26

VI Film 29

Specialty Paper 30

Specialty Film 32

Durables Film 35

Adhesive

Comparison table 38

General Purpose – Papers 40

General Purpose – Films. 45

Special Purpose 48

Liner

Liner contents 56

Glassine. 57

PET 58

Kraft 59

Product Selection Considerations. . . 60



How to Use this Guide

Facestock

Basis Weight

The average weight of the liner in grams per square meter of material.

Thickness

The thickness of the facestock in microns.

FSC® Certification

Products that have been certified by the Forest Stewardship Council® are marked with this symbol 



The mark of
responsible forestry

Adhesive

Initial Tack

Defines the degree to which the product adheres to the substrate on first contact.

Ultimate Adhesion

Identifies the long-term adhesive strength.

Minimum Application Temperature

The minimum temperature at the time of application of the label. The substrate must be clean at the time of application.

Service Temperature Range

The range of temperatures within which the properties of the applied label are substantially unchanged over a prolonged period of time. The actual duration and temperature extremes depend also on the type of face material used, the substrate and environment.

Applications

- **Freezer**
Adhesives suitable for application to substrates at temperatures down to -20°C
- **Chilled**
Suitable for use on dry surfaces that may be exposed to condensation after application.
- **Wet Surfaces**
Suitable for use on surfaces where partially exposed to limited moisture or condensation.
- **Tight Mandrel**
Suitable for low diameter substrates greater than 15mm on glass and PE. Prior testing is highly recommended.
- **Ice Bucket**
Suitable for submersion in ice bucket for periods of up to 2 hours.

Liner

Basis Weight

The average weight of the liner in grams per square meter of material.

Thickness

The thickness of the facestock in microns.

FSC® Certification

Products that have been certified by the Forest Stewardship Council® are marked with this symbol 



Important Information

Avery Dennison provides a broad range of solutions from Paper to Films, with many different adhesives available for different application needs.

Critical Substrates

Substances such as textiles, plasticised vinyls, apolar and rough surfaces.

Food Contact Status

For direct or indirect contact to food, adhesives must be certified to comply with international standards. The two most widely recognised standards are:

- **FDA (Food and Drug Administration) from the United States.**
 - Indirect food contact (separated by a functional barrier) – FDA 21CFR175.105
 - Direct contact to poultry, dry food, and processed, frozen, dried, or partially dehydrated fruits and vegetables – FDA 21CFR175.125 (a)
 - Direct food contact to raw fruit and raw vegetables – FDA 21CFR175.125 (b)
- **BfR (Federal Institute for Risk Assessment) from Germany.**
 - Direct contact with dry and moist non fatty foodstuffs for Plastic Dispersions (e.g., acrylic emulsion adhesives) – Bfr XIV
 - Direct contact with dry and moist non fatty foodstuffs for Natural & Synthetic rubbers (e.g., hot melt adhesives) – Bfr XXI

A number of Avery Dennison's adhesives are certified to these standards. Please contact your local Avery Dennison representative for an up-to-date listing of food-certified adhesives.

Quality Assurance

Avery Dennison self-adhesive materials are manufactured to high quality standards and are certified to ISO 9001:2008.

Regulations and Specifications

Many Avery Dennison products have been tested to, and meet the various requirements of important regulations and international specifications such as toy labelling, labels for marine use, food labelling, industrial specifications, etc. Details can be made available upon request for each individual product.



Recommended Storage Conditions

- Store at a temperature of 20-25°C and a relative humidity of 40-50%.
- Original Packaging.
- Away from direct sunlight.
- Store reels of printed labels horizontally.
- Rotate stocks so that oldest material is used first.
- Ensure that winding tension of printed label reels is not too tight in order to prevent adhesive bleed.
- Repack partly-used reels of raw material or printed labels in their original packaging or identical packaging material.

Important Notice

Information on physical and chemical characteristics is based upon tests we believe to be reliable. The values are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine, prior to use, the suitability of any material for a specific purpose.

Warranty

Avery Dennison products are manufactured under careful quality control and are warranted to be free from defect in materials and workmanship. Any material shown to our satisfaction to be defective at the time of delivery will be compensated as per local country policy on the roll(s) returned. The manufacturer will not be responsible for claims beyond replacement of the material. No sales person, representative or agent is authorised to give any guarantee, warranty or make any representation contrary to the foregoing. All products described herein are sold subject to Avery Dennison's standard conditions of sale, a copy of which is available upon request.

Environmental Aspects

Avery Dennison is committed to protecting the environment and manufacturing safe products. We are actively involved in a continuous search for base materials and manufacturing technologies that have the least possible impact on the environment. For information on individual products or components please contact your Avery Dennison representative.

Disclaimer Information

Specific products must be used for the following applications – hot-fill or freshly blown molded bottles, blood bags, and products for primary food contact. Outdoor use of PVCs (due to plasticiser migration) and synthetic films when exposure to direct UV light can in no way be guaranteed. Check with Marketing on recommended life. Wine labels – The selection of suitable varnishes for white wine applications needs to be made in conjunction with your ink supplier and with the knowledge that uncoated paper stocks will exhibit higher moisture ingress versus alternative substrates.



Facestock



Facestock contents

Quick Compare Guide	10
-------------------------------	----

Prime Paper

Cast Coated	12
High Gloss Paper	
High Gloss Elite FSC 	
Gloss Plus FSC 	
Machine Coated	13
MC Prime FSC 	
MC Primecoat GP FSC 	
MC Elite FSC 	
LW 60 FSC 	
Uncoated	14
Vellum	
Vellum Elite FSC 	

Prime Film

Polyethylene (PE) - Clear	15
PE85 Top Trans	
PE85 NTC Trans	
PE75 NTC Trans	
Polyethylene (PE) - White	16
PE85 Top White	
PE85 NTC White	
PE75 NTC White	
Polyethylene (PE) - Metalized	16
Bright Silver PE85 TC	
Polypropylene (PP) - Clear	17
PPNg Top Trans	
PP50 TC Clear	
PP50 NTC Clear	
PP40 Top Clear	
PP30 Clear TC	
PP30 Clear NTC	
Overlaminating Gloss PP	
Overlaminating Matte PP	
Polypropylene (PP) - White	20
PP50 Top White	
PPNg Top Pearlized White	
PP60 Top White	
rPP Top White	
PP50 Top Pearlized White	
PP40 Top White	
Opalux 55	



Prime Film (continued)

Polypropylene (PP) - Metalized . . . 23

[PP50 Silver TC](#)
[PP TC Silver Elite](#)
[PP40 Top Silver](#)

Polyolefin (PO) - Clear 24

[Flex+ Clear NTC](#)

Polyolefin (PO) - White 23

[Flex+ White NTC](#)

Synthetic Paper 25

[Synthetic Paper](#)
[Synthetic Paper 65](#)
[PP Top Matte White](#)

VI Paper

Direct Thermal 26

[Direct Thermal Premium FSC](#) 
[Direct Thermal 200GP FSC](#) 
[Direct Thermal 200WS FSC](#) 
[Direct Thermal 200ST FSC](#) 
[Direct Thermal 60 TC FSC](#) 
[Direct Thermal 150RL FSC](#) 
[rDirect Thermal 300LD FSC](#) 
[Baggage Tag FSC](#) 
[Baggage Tag Elite FSC](#) 

Thermal Transfer 28

[Transtherm 2C FSC](#) 
[Transtherm Plus FSC](#) 
[TT Elite FSC](#) 

Laser/Inkjet Paper 28

[LCJ Premium FSC](#) 

VI Film

Direct Thermal 29

[Baggage Tag 300BA](#)
[Direct Thermal PP 300BL](#)



Specialty Paper

Foil	30
Matte Silver Foil FSC 	
Bright Silver Foil FSC 	
Radiants	30
Radiants Range FSC 	
Wine - Uncoated Paper	31
Vintage FSC 	
Estate #4 PE FSC 	
Estate #8 PE FSC 	
Artisan Plus FSC 	
KW Gen 3 PE FSC 	

Specialty Film

Polypropylene (PP) - White	32
PP40 Top Matte White	
Synthetic Paper	32
Synthetic Paper TR75	
Synthetic Paper II	
3 Mil Synthetic Paper	
rSynthetic Paper	
WBIJ Synthetic Paper	
Polypropylene (PP) - White	34
WBIJ PP Top Gloss White	
Polyester (PET) - Clear	34
1M Clear PET TC	
PET Top Clear	

Durables Film

Polyester (PET) - White	35
2M White PET TC	
75µm Matte White PET TC	
50µm Matte White PET TC	
Polyester (PET) - Metalized	36
50µm Bright Silver PET TC	
2M Matte Ch PET TC	
1M Matte Ch PET TC	
Copy Code CH PET Plus	
Polyester (PETC) - White	36
2M WH PETC TC	



Facestock / Quick Compare Guide

Prime Paper		Printability	Water Resistance	OBA	Stiffness	Tensile Strength
Cast Coated	High Gloss Paper	★★★★★	★★★	Yes	★★★★☆	★★★★☆
	High Gloss Elite FSC 	★★★★★	★★★	Yes	★★★★☆	★★★★☆
	Gloss Plus FSC 	★★★★★	★★★	Yes	★★★★☆	★★★★☆
Machine Coated	MC Prime FSC 	★★★★☆	★★★	Yes	★★★☆☆	★★★☆☆
	MC Primecoat GP FSC 	★★★★★	★★	Yes	★★★★	★★★★☆
	MC Elite FSC 	★★★★★	★★★	Yes	★★☆☆	★★★★
	LW 60 FSC 	★★★★★	★★	Yes	★★	★★☆☆
Uncoated	Vellum	★★★	-	Yes	★★★★	★★
	Vellum Elite FSC 	★★★	-	Yes	★★★★	★★

Prime Film - Clear		Printability	Stiffness	Conformability
Polyethylene (PE)	PE85 Top Trans	★★★★★	★★★	★★★★★
	PE85 NTC Trans	★★★★★	★★★	★★★★★
	PE75 NTC Trans	★★★★★	★★★	★★★★★
Polypropylene (PP)	PPNg Top Trans	★★★★★	★★★★★	★★
	PP50 TC Clear	★★★★★	★★★★★	★★
	PP50 NTC Clear	★★★	★★★★★	★★
	PP40 Top Clear	★★★★★	★★★★	★★★
	PP30 Clear TC	★★★★★	★★★	★★★
	PP30 Clear NTC	★★★	★★★	★★★
	Overlaminating Gloss PP	★★	★★	★★★
	Overlaminating Matte PP	★★	★★	★★★
Polyolefin (PO)	Flex+ Clear NTC	★★★★★	★★★★★	★★★★★

Prime Film - White		Printability	Stiffness	Conformability
Polyethylene (PE)	PE85 Top White	★★★★★	★★★	★★★★★
	PE85 NTC White	★★★★★	★★★	★★★★★
	PE75 NTC White	★★★★★	★★★	★★★★★
Polypropylene (PP)	PP50 Top White	★★★★★	★★★★★	★★☆☆
	PPNg Top Pearlized White	★★★★★	★★★★☆	★★
	PP60 Top White	★★★★★	★★★★☆	★★
	rPP Top White	★★★★★	★★★★☆	★★
	PP50 Top Pearlized White	★★★★★	★★★★☆	★★★
	PP40 Top White	★★★★★	★★★★☆	★★★
	Opalux 55	★★★	★★★★★	★★☆☆
	Flex+ White NTC	★★★★★	★★★★★	★★★★★
Synthetic Paper	Synthetic Paper	★★★★★	★★★★★	★★
	Synthetic Paper 65	★★★★★	★★★★☆	★★
	PP Top Matte White	★★★★★	★★★★☆	★★



Prime Film - Metalized

		Printability	Stiffness	Conformability
Polyethylene (PE)	Bright Silver PE85 TC	★★★★★	★★★	★★★★★
Polypropylene (PP)	PP50 Silver TC	★★★★	★★★★★	★★
	PP TC Silver Elite	★★★★☆	★★★★	★★☆
	PP40 Top Silver	★★★★	★★★★	★★★

Variable Information Papers

		Print Definition	Print Durability
Direct Thermal	Direct Thermal Premium FSC	★★★★★	★★★
	Direct Thermal 200GP FSC	★★★★	★★☆
	Direct Thermal 200WS FSC	★★★★	★★☆
	Direct Thermal 200ST FSC	★★★★	★★☆
	Direct Thermal 60 TC FSC	★★★★	★★☆
	Direct Thermal 150RL FSC	★★★	★★
	rDirect Thermal 300LD FSC	★★☆	★☆
Thermal Transfer	Transtherm 2C FSC	★★★★★	★★★★★
	Transtherm Plus FSC	★★★★	★★★★

Specialty/Durables Films

		Printability	Stiffness	Conformability
Synthetic Paper	Synthetic Paper II	★★★★☆	★★★★★	★★
	Synthetic Paper TR75	★★★★★	★★★★☆	★★
	3 Mil Synthetic Paper	★★★★	★★★★☆	★★
Polyester	1M Clear PET TC	★★★★★	★★★	-
	2M White PET TC	★★★★★	★★★★	-
	75µm Matte White PET TC	★★★★	★★★★★	-
	50µm Matte White PET TC	★★★★	★★★★	-
	50µm Bright Silver PET TC	★★★★	★★★★	-
	2M Matte Ch PET TC	★★★★★	★★★★	-
	1M Matte Ch PET TC	★★★★★	★★★	-
	Copy Code CH PET Plus	★★★	★★★★	-
	2M WH PETC TC	★★★★	★★★★☆	-

★★★★★ Excellent

★★★★ Very Good

★★★ Good

★★ Fair

- Not Applicable



Facestock / Prime Paper

Cast Coated

High Gloss Paper

A white, one side gloss finished cast coated paper.

- Suitable for a wide range of promotional and industrial labels whereby brilliant multicolour print quality and attractive gloss appearance are required.
- Typical applications include labels for use in the cosmetic, pharmaceutical, food industry, chemical products and promotional labels.

Basis Weight	80 g/m ²
Thickness	88 µm
Printability	★★★★★
Water Resistance	★★★
OBA	Yes
Stiffness	★★★★☆
Tensile Strength	★★★★☆

High Gloss Elite FSC

An FSC® certified white, one-side cast coated, gloss finished woodfree printing paper.

- High gloss coating giving brilliant multicolour print quality and attractive gloss appearance,
- Typical applications include labels for cosmetic, pharmaceutical, food products and promotional labels.

Basis Weight	80 g/m ²
Thickness	84 µm
Printability	★★★★★
Water Resistance	★★★
OBA	Yes
Stiffness	★★★★☆
Tensile Strength	★★★★☆

Gloss Plus FSC

An FSC® certified white, high gloss finished woodfree printing paper

- Designed with superior print gloss for applications whereby attractive gloss appearance is required.
- Excellent print gloss can be achieved by suitable varnish. Thinner and lighter facestock with added conformability.
- Typical applications include labels for cosmetic, pharmaceutical, food products and promotional labels.

Basis Weight	80 g/m ²
Thickness	70 µm
Printability	★★★★★
Water Resistance	★★★
OBA	Yes
Stiffness	★★★★☆
Tensile Strength	★★★★☆



Facestock / Prime Paper (continued)

Machine Coated

MC Prime FSC

An FSC® certified semi-gloss, one side machine coated, calendered white printing paper.

- Suitable for a wide range of promotional and industrial labels applications whereby attractive semi-gloss appearance with heavy multicolor ink coverage work is required.
- Typical applications include labels for cosmetic, pharmaceutical and food products industry.

Basis Weight	80 g/m ²
Thickness	70 µm
Printability	★★★★☆
Water Resistance	★★★
OBA	Yes
Stiffness	★★★☆
Tensile Strength	★★★☆

MC Primecoat GP FSC

An FSC® certified semi-gloss, machine coated, calendered white printing paper.

- Good gloss appearance and suitable for heavy multicolor ink coverage work.
- Typical applications include labels for cosmetic, pharmaceutical and food products industry.

Basis Weight	80 g/m ²
Thickness	63 µm
Printability	★★★★
Water Resistance	★★
OBA	Yes
Stiffness	★★★
Tensile Strength	★★★☆

MC Elite FSC

An FSC® certified semi-gloss, machine coated, calendered white printing paper.

- Suitable for a wide range of promotional and industrial labels applications whereby attractive semi-gloss appearance with heavy multicolor ink coverage work is required.
- Typical applications include labels for cosmetic, pharmaceutical and food products industry.

Basis Weight	70 g/m ²
Thickness	61 µm
Printability	★★★★
Water Resistance	★★★
OBA	Yes
Stiffness	★★☆
Tensile Strength	★★★

LW 60 FSC

An FSC® certified semi-gloss, one side machine coated, calendered white printing paper.

- Low memory, makes it ideal for tight mandrel applications such as labelling small cylindrical substrates.
- Provides excellent functionality for labelling pharmaceuticals in vials, syringes, dropper bottles, etc.

Basis Weight	60 g/m ²
Thickness	52 µm
Printability	★★★★
Water Resistance	★★
OBA	Yes
Stiffness	★★
Tensile Strength	★★☆



Facestock / Prime Paper (continued)

Uncoated

Vellum

A white, machine finished, woodfree-printing paper.

- Designed for the manufacture of continuous forms products for use in high speed impact printers.
- Excellent fanfolding and refanfolding properties, even in high speed wide web EDP printers.
- The facestock's surface structure provides excellent print resolution.
- Ideal for label applications requiring variable information.

Basis Weight	70 g/m ²
Thickness	90 µm
Printability	★★★
Water Resistance	-
OBA	Yes
Stiffness	★★★
Tensile Strength	★★

Vellum Elite FSC

An FSC® certified white, machine finished, woodfree-printing paper.

- Typical applications for this product include industrial labeling, supermarkets, food packaging, catch-weight, cosmetics, toiletries, chemical products and promotional labeling.
- Designed to give optimum performance by giving very good results with heavy ink coverage printing while still maintaining enough opacity required for the applications.

Basis Weight	60 g/m ²
Thickness	78 µm
Printability	★★★
Water Resistance	-
OBA	Yes
Stiffness	★★★
Tensile Strength	★★



Facestock / Prime Film

Polyethylene (PE) - Clear

PE85 Top Trans

A blown co-extruded, transparent polyethylene film with a print receptive top coating

- Applications are predominantly in home and personal care, requiring durability in end-use with resistance to moisture and content overspill.
- Due to its flexibility, the product is suitable for applications requiring squeezability and conformability, it can be used on substrates such as squeezable bottles and other flexible containers.
- Can be used for applications where PVC labels are not wanted for environmental reasons.

Basis Weight	78 g/m ²
Thickness	82 µm
Printability	★★★★★
Stiffness	★★★
Conformability	★★★★★

PE85 NTC Trans

A blown co-extruded, corona-treated transparent polyethylene film

- Applications are predominantly in home and personal care, requiring durability in end-use with resistance to moisture and content overspill.
- Due to its flexibility, the product is suitable for applications requiring squeezability and conformability, it can be used on substrates such as squeezable bottles and other flexible containers.
- Can be used for applications where PVC labels are not wanted for environmental reasons.

Basis Weight	77 g/m ²
Thickness	82 µm
Printability	★★★★★
Stiffness	★★★
Conformability	★★★★★

PE75 NTC Trans

A blown co-extruded, corona-treated transparent polyethylene film

- Applications are predominantly in home and personal care, requiring durability in end-use with resistance to moisture and content overspill.
- Due to its flexibility, the product is suitable for applications requiring squeezability and conformability, it can be used on substrates such as squeezable bottles and other flexible containers.
- Can be used for applications where PVC labels are not wanted for environmental reasons.

Basis Weight	70 g/m ²
Thickness	75 µm
Printability	★★★★★
Stiffness	★★★
Conformability	★★★★★



Facestock / Prime Film (continued)

Polyethylene (PE) - White

PE85 Top White

A blown co-extruded, white polyethylene film with a print receptive top coating

- Applications are predominantly in home and personal care, requiring durability in end-use with resistance to moisture and content overspill.
- Due to its flexibility, the product is suitable for applications requiring squeezability and conformability, it can be used on substrates such as squeezable bottles and other flexible containers.
- Can be used for applications where PVC labels are not wanted for environmental reasons.

Basis Weight	82 g/m ²
Thickness	82 µm
Printability	★★★★★
Stiffness	★★★
Conformability	★★★★★

PE85 NTC White

A blown co-extruded, corona-treated white polyethylene film

- Applications are predominantly in home and personal care, requiring durability in end-use with resistance to moisture and content overspill.
- Due to its flexibility, the product is suitable for applications requiring squeezability and conformability, it can be used on substrates such as squeezable bottles and other flexible containers.
- Can be used for applications where PVC labels are not wanted for environmental reasons.

Basis Weight	82 g/m ²
Thickness	82 µm
Printability	★★★★
Stiffness	★★★
Conformability	★★★★★

PE75 NTC White

A blown co-extruded, corona-treated white polyethylene film

- Applications are predominantly in home and personal care, requiring durability in end-use with resistance to moisture and content overspill.
- Due to its flexibility, the product is suitable for applications requiring squeezability and conformability, it can be used on substrates such as squeezable bottles and other flexible containers.
- Can be used for applications where PVC labels are not wanted for environmental reasons.

Basis Weight	74 g/m ²
Thickness	75 µm
Printability	★★★★
Stiffness	★★★
Conformability	★★★★★

Polyethylene (PE) - Metalized

Bright Silver PE85 TC

A bright metallic polyethylene film with a print receptive top coating on the metallised surface

- Applications are predominantly in home and personal care, requiring durability in end-use with resistance to moisture and content overspill.
- Due to its flexibility, the product is suitable for applications requiring squeezability and conformability, it can be used on substrates such as squeezable bottles and other flexible containers.
- Can be used for applications where PVC labels are not wanted for environmental reasons.

Basis Weight	78 g/m ²
Thickness	85 µm
Printability	★★★★★
Stiffness	★★★
Conformability	★★★★★



Facestock / Prime Film (continued)

Polypropylene (PP) – Clear

PPNg Top Trans

A bi-axially oriented, glossy transparent polypropylene film with a print-receptive top coating

- Applications are predominantly in market segments where rigid containers are used.
- Suitable for labelling of quality products such as cosmetics, toiletries, luxury articles, promotional labeling, automotive lubricants and household chemicals where durability and resistance to moisture or chemicals are required.
- Ideal for applications requiring 'substrate identical labeling' on polypropylene containers and in environmentally sensitive markets requiring recycling of 'polyolefin' packs.
- Due to fairly rigid nature of polypropylene, care should be taken with the use on 'non-uniform' surfaces or where a high level of squeezability is desired.

Basis Weight	46 g/m ²
Thickness	50 µm
Printability	★★★★★
Stiffness	★★★★★
Conformability	★★

PP50 TC Clear

A bi-axially oriented, glossy transparent polypropylene film with a print-receptive top coating

- Applications are predominantly in market segments where rigid containers are used.
- Suitable for labelling of quality products such as cosmetics, toiletries, luxury articles, promotional labeling, automotive lubricants and household chemicals where durability and resistance to moisture or chemicals are required.
- Ideal for applications requiring 'substrate identical labeling' on polypropylene containers and in environmentally sensitive markets requiring recycling of 'polyolefin' packs.
- Not suitable for application where re-positionability is required.
- Due to fairly rigid nature of polypropylene, care should be taken with the use on 'non-uniform' surfaces or where a high level of squeezability is desired.

Basis Weight	46 g/m ²
Thickness	50 µm
Printability	★★★★★
Stiffness	★★★★★
Conformability	★★

PP50 NTC Clear

A biaxially oriented, glossy transparent polypropylene film with corona-treated print skin layer

- Applications are predominantly in market segments where rigid containers are used.
- Suitable for labelling of quality products such as cosmetics, toiletries, luxury articles, promotional labeling, automotive lubricants and household chemicals where durability and resistance to moisture or chemicals are required.
- Ideal for applications requiring 'substrate identical labeling' on polypropylene containers and in environmentally sensitive markets requiring recycling of 'polyolefin' packs.
- Due to fairly rigid nature of polypropylene, care should be taken with the use on 'non-uniform' surfaces or where a high level of squeezability is desired.

Basis Weight	45 g/m ²
Thickness	50 µm
Printability	★★★
Stiffness	★★★★★
Conformability	★★



Facestock / Prime Film (continued)

Polypropylene (PP) – Clear (continued)

PP40 Top Clear

A bi-axially oriented, glossy transparent polypropylene film with a print-receptive top coating

- Applications are predominantly in market segments where rigid containers are used.
- Suitable for labelling of quality products such as cosmetics, toiletries, luxury articles, promotional labeling, automotive lubricants and household chemicals where durability and resistance to moisture or chemicals are required.
- Ideal for applications requiring 'substrate identical labeling' on polypropylene containers and in environmentally sensitive markets requiring recycling of 'polyolefin' packs.
- Due to fairly rigid nature of polypropylene, care should be taken with the use on 'non-uniform' surfaces or where a high level of squeezability is desired.

Basis Weight	37 g/m ²
Thickness	40 µm
Printability	★★★★★
Stiffness	★★★★
Conformability	★★★

PP30 Clear TC

A bi-axially oriented, glossy transparent polypropylene film with a print receptive top coating

- Ideal for daily, food and household product packaging.
- Ideal for applications requiring 'substrate identical labeling' on polypropylene containers and in environmentally sensitive markets requiring recycling of 'polyolefin' packs.
- Due to fairly rigid nature of polypropylene, care should be taken with the use on 'non-uniform' surfaces or where a high level of squeezability is desired.

Basis Weight	27 g/m ²
Thickness	30 µm
Printability	★★★★
Stiffness	★★★
Conformability	★★★

PP30 Clear NTC

A biaxially oriented, glossy transparent corona treated polypropylene film

- Ideal for daily, food and household product packaging.
- Ideal for applications requiring 'substrate identical labeling' on polypropylene containers and in environmentally sensitive markets requiring recycling of 'polyolefin' packs.
- Due to fairly rigid nature of polypropylene, care should be taken with the use on 'non-uniform' surfaces or where a high level of squeezability is desired.

Basis Weight	27 g/m ²
Thickness	30 µm
Printability	★★★
Stiffness	★★★
Conformability	★★★



Facestock / Prime Film (continued)

Polypropylene (PP) - Clear (continued)

Overlaminating Gloss PP

A bi-axially oriented, glossy transparent polypropylene film

- Suitable for use as an overlaminating film providing maximum protection to both film and paper base materials.
- However, depending on the aesthetic requirements, this construction may not be suitable as an overlaminate on dark printed background film labels.

Basis Weight	18 g/m ²
Thickness	20 µm
Printability	★★
Stiffness	★★
Conformability	★★★

Overlaminating Matte PP

A bi-axially oriented, matte transparent polypropylene film

- Suitable for use as an overlaminating film providing maximum protection to both film and paper base materials.
- However, depending on the aesthetic requirements, this construction may not be suitable as an overlaminate on dark printed background film labels.

Basis Weight	17 g/m ²
Thickness	20 µm
Printability	★★
Stiffness	★★
Conformability	★★★



Facestock / Prime Film (continued)

Polypropylene (PP) – White

PP50 Top White

A bi-axially oriented, glossy white polypropylene film with a print-receptive top coating

- Applications are predominantly in market segments where rigid containers are used.
- Suitable for labelling of quality products such as cosmetics, toiletries, luxury articles, promotional labeling, automotive lubricants and household chemicals where durability and resistance to moisture or chemicals are required.
- Ideal for applications requiring 'substrate identical labeling' on polypropylene containers and in environmentally sensitive markets requiring recycling of 'polyolefin' packs.
- Due to fairly rigid nature of polypropylene, care should be taken with the use on 'non-uniform' surfaces or where a high level of squeezability is desired.

Basis Weight	50 g/m ²
Thickness	50 µm
Printability	★★★★★
Stiffness	★★★★
Conformability	★★☆

PPNg Top Pearlized White

A bi-axially oriented, glossy, pearlized white polypropylene film with a print-receptive top coating.

- Applications are predominantly in market segments where rigid containers are used.
- Suitable for labelling of quality products such as cosmetics, toiletries, luxury articles, promotional labeling, automotive lubricants and household chemicals where durability and resistance to moisture or chemicals are required.
- The "pearlized white" appearance of the facestock gives a unique and premium look offering excellent shelf appeal.
- Ideal for applications requiring 'substrate identical labeling' on polypropylene containers and in environmentally sensitive markets requiring recycling of 'polyolefin' packs.
- Due to fairly rigid nature of polypropylene, care should be taken with the use on 'non-uniform' surfaces or where a high level of squeezability is desired.

Basis Weight	45 g/m ²
Thickness	60 µm
Printability	★★★★★
Stiffness	★★★★☆
Conformability	★★

PP60 Top White

A bi-axially oriented, glossy white polypropylene film with a print-receptive top coating

- Applications are predominantly in market segments where rigid containers are used.
- Suitable for labelling of quality products such as cosmetics, toiletries, luxury articles, promotional labeling, automotive lubricants and household chemicals where durability and resistance to moisture or chemicals are required.
- Ideal for applications requiring 'substrate identical labeling' on polypropylene containers and in environmentally sensitive markets requiring recycling of 'polyolefin' packs.
- Due to fairly rigid nature of polypropylene, care should be taken with the use on 'non-uniform' surfaces or where a high level of squeezability is desired.

Basis Weight	44 g/m ²
Thickness	60 µm
Printability	★★★★★
Stiffness	★★★★☆
Conformability	★★



Facestock / Prime Film (continued)

Polypropylene (PP) – White (continued)

rPP Top White

A bi-axially oriented, glossy white polypropylene film with a print-receptive top coating. Film contains 30% recycled content.

- The recycled PP film contains 30% recycled content, making this a more sustainable label option, helping brands achieve higher recycled content in the packaging.
- Applications are predominantly in market segments where rigid containers are used.
- Suitable for labelling of quality products such as cosmetics, toiletries, luxury articles, promotional labeling, automotive lubricants and household chemicals where durability and resistance to moisture or chemicals are required.
- Ideal for applications requiring 'substrate identical labeling' on polypropylene containers and in environmentally sensitive markets requiring recycling of 'polyolefin' packs.
- Due to fairly rigid nature of polypropylene, care should be taken with the use on 'non-uniform' surfaces or where a high level of squeezability is desired.

Basis Weight	42 g/m ²
Thickness	65 µm
Printability	★★★★★
Stiffness	★★★★☆
Conformability	★★

PP50 Top Pearlized White

A bi-axially oriented, glossy, pearlized white polypropylene film with a print-receptive top coating.

- Applications are predominantly in market segments where rigid containers are used.
- Suitable for labelling of quality products such as cosmetics, toiletries, luxury articles, promotional labeling, automotive lubricants and household chemicals where durability and resistance to moisture or chemicals are required.
- The "pearlized white" appearance of the facestock gives a unique and premium look offering excellent shelf appeal.
- Ideal for applications requiring 'substrate identical labeling' on polypropylene containers and in environmentally sensitive markets requiring recycling of 'polyolefin' packs.
- Due to fairly rigid nature of polypropylene, care should be taken with the use on 'non-uniform' surfaces or where a high level of squeezability is desired.

Basis Weight	36 g/m ²
Thickness	50 µm
Printability	★★★★★
Stiffness	★★★☆☆
Conformability	★★★

PP40 Top White

A bi-axially oriented, glossy white polypropylene film with a print-receptive top coating

- Applications are predominantly in market segments where rigid containers are used.
- Suitable for labelling of quality products such as cosmetics, toiletries, luxury articles, promotional labeling, automotive lubricants and household chemicals where durability and resistance to moisture or chemicals are required.
- Ideal for applications requiring 'substrate identical labeling' on polypropylene containers and in environmentally sensitive markets requiring recycling of 'polyolefin' packs.
- Due to fairly rigid nature of polypropylene, care should be taken with the use on 'non-uniform' surfaces or where a high level of squeezability is desired.

Basis Weight	40 g/m ²
Thickness	40 µm
Printability	★★★★★
Stiffness	★★★★☆
Conformability	★★★



Facestock / Prime Film (continued)

Polypropylene (PP) – White (continued)

Opalux 55

A bi-axially oriented, glossy white polypropylene film with corona-treated print skin layer

- Applications are predominantly in market segments where rigid containers are used.
- Suitable for labelling of quality products such as cosmetics, toiletries, luxury articles, promotional labeling, automotive lubricants and household chemicals where durability and resistance to moisture or chemicals are required.
- Ideal for applications requiring 'substrate identical labeling' on polypropylene containers and in environmentally sensitive markets requiring recycling of 'polyolefin' packs.
- Due to fairly rigid nature of polypropylene, care should be taken with the use on 'non-uniform' surfaces or where a high level of squeezability is desired.

Basis Weight	39 g/m ²
Thickness	56 µm
Printability	★★★
Stiffness	★★★★★
Conformability	★★☆



Facestock / Prime Film (continued)

Polypropylene (PP) – Metalized

PP50 Silver TC

A bi-axially oriented, glossy bright metallised polypropylene film with a print-receptive top coating

- Applications are predominantly in market segments where rigid containers are used.
- Suitable for labelling of quality products such as cosmetics, toiletries, luxury articles, promotional labeling, automotive lubricants and household chemicals where durability and resistance to moisture or chemicals are required.
- Can be used as a cost effective alternative to metallic foil blocking.
- Ideal for applications requiring 'substrate identical labeling' on polypropylene containers and in environmentally sensitive markets requiring recycling of 'polyolefin' packs.
- Due to fairly rigid nature of polypropylene, care should be taken with the use on 'non-uniform' surfaces or where a high level of squeezability is desired.

Basis Weight	47 g/m ²
Thickness	50 µm
Printability	★★★★
Stiffness	★★★★★
Conformability	★★

PP TC Silver Elite

A bi-axially oriented, glossy bright metallised polypropylene film with a print-receptive top coating

- Applications are predominantly in market segments where rigid containers are used.
- Suitable for labelling of quality products such as cosmetics, toiletries, luxury articles, promotional labeling, automotive lubricants and household chemicals where durability and resistance to moisture or chemicals are required.
- Can be used as a cost effective alternative to metallic foil blocking.
- Ideal for applications requiring 'substrate identical labeling' on polypropylene containers and in environmentally sensitive markets requiring recycling of 'polyolefin' packs.
- Due to fairly rigid nature of polypropylene, care should be taken with the use on 'non-uniform' surfaces or where a high level of squeezability is desired.

Basis Weight	41 g/m ²
Thickness	47 µm
Printability	★★★★☆
Stiffness	★★★★★
Conformability	★★☆

PP40 Top Silver

A bi-axially oriented, glossy bright metallised polypropylene film with a print-receptive top coating

- Applications are predominantly in market segments where rigid containers are used.
- Suitable for labelling of quality products such as cosmetics, toiletries, luxury articles, promotional labeling, automotive lubricants and household chemicals where durability and resistance to moisture or chemicals are required.
- Can be used as a cost effective alternative to metallic foil blocking.
- Ideal for applications requiring 'substrate identical labeling' on polypropylene containers and in environmentally sensitive markets requiring recycling of 'polyolefin' packs.
- Due to fairly rigid nature of polypropylene, care should be taken with the use on 'non-uniform' surfaces or where a high level of squeezability is desired.

Basis Weight	36 g/m ²
Thickness	40 µm
Printability	★★★★
Stiffness	★★★★★
Conformability	★★★



Facestock / Prime Film (continued)

Polyolefin (PO) - Clear

Flex+ Clear NTC

A corona-treated, flexible, co-extruded clear polyolefin film

- Designed for the prime label market, specifically the cosmetics, home and personal care segments, where clarity, conformability and adhesion to HDPE and PET containers are required.
- Recommended for those markets that require the recycling of polyolefin containers.
- Designed for the “No-Label” look decoration.

Basis Weight	50 g/m ²
Thickness	55 µm
Printability	★★★★
Stiffness	★★★★
Conformability	★★★★

Polyolefin (PO) - White

Flex+ White NTC

A corona-treated, flexible, co-extruded white polyolefin film

- Designed for the prime label market, specifically the cosmetics, home and personal care segments, where clarity, conformability and adhesion to HDPE and PET containers are required.
- Recommended for those markets that require the recycling of polyolefin containers.

Basis Weight	50 g/m ²
Thickness	55 µm
Printability	★★★★
Stiffness	★★★★
Conformability	★★★★



Facestock / Prime Film (continued)

Synthetic Paper

Synthetic Paper

A matte white, high opacity polypropylene film which is suitable for flexographic, letterpress, screen & thermal transfer printing and has high strength and durability as well as good moisture and chemical resistance.

- Gives excellent printing performance in thermal transfer printing as well as conventional printing techniques.
- Suitable ribbon and print setting should be carefully selected to achieve optimum thermal transfer print performance.
- Can be printed well with flexographic, letterpress and screen printing techniques.
- Due to semi-rigid nature of polypropylene, care should be taken with 'non-uniform' surfaces or highly squeezable applications.
- Suitable for use in a wide range of durable labeling applications whereby UL recognition (Indoor Service) is required

Basis Weight	68 g/m ²
Thickness	75 µm
Printability	★★★★★
Stiffness	★★★★★
Conformability	★★

Synthetic Paper 65

A matte white, high opacity polypropylene film which is suitable for conventional and thermal transfer printing, with durability and good moisture resistance.

- The facestock can be printed with conventional printing techniques.
- This product also gives excellent thermal transfer printing performance when matched with the correct ribbon and print setting.
- Product with high strength and good moisture resistance.
- Therefore, this product can be used for applications requiring durable, variable information labels.
- Due to semi-rigid nature of polypropylene, care should be taken with 'non uniform' surfaces or highly squeezable applications. This product is suitable for use in a wide range of durable labeling applications.

Basis Weight	51 g/m ²
Thickness	65 µm
Printability	★★★★★
Stiffness	★★★★☆
Conformability	★★

PP Top Matte White

A bi-axially oriented, high opacity, matte white polypropylene film with a print-receptive top coating

- Applications are predominantly in market segments where rigid containers are used.
- Suitable for labelling of quality products such as cosmetics, toiletries, luxury articles, promotional labeling, automotive lubricants and household chemicals where durability and resistance to moisture or chemicals are required.
- The "matte white" appearance of the facestock gives a unique and premium look offering excellent shelf appeal.
- The facestock can be printed well with conventional printing techniques and with thermal transfer printing, when matched with the correct ribbon. Therefore this product is suitable for variable information labels applications.
- Ideal for applications requiring 'substrate identical labeling' on polypropylene containers and in environmentally sensitive markets requiring recycling of 'polyolefin' packs.
- Due to fairly rigid nature of polypropylene, care should be taken with the use on 'non-uniform' surfaces or where a high level of squeezability is desired.

Basis Weight	54 g/m ²
Thickness	75 µm
Printability	★★★★★
Stiffness	★★★★☆
Conformability	★★



Facestock / VI Paper

Direct Thermal

Direct Thermal Premium FSC

An FSC® certified, smooth, bright, white woodfree paper with a barrier coated thermosensitive layer.

- Offers excellent resistance to moisture, fat, oil, etc.
- Typical applications include barcode labels for pre-packed food (e.g. meat, fish, poultry, cheese) and industrial barcoding (e.g. tracking, shelf edge, laboratory, hospital) whereby a high level of image resistance is required.

Basis Weight	74 g/m ²
Thickness	77 µm
Print Definition	★★★★★
Print Durability	★★★

Direct Thermal 200GP FSC

An FSC® certified, smooth, white woodfree paper with a barrier coated thermosensitive layer.

- Designed with essential resistance to oil, water and heat suited for pre-packed food.
- Typical applications include barcode labels for typical weight scale applications where moderate to high barcode image is required.

Basis Weight	76 g/m ²
Thickness	80 µm
Print Definition	★★★★★
Print Durability	★★☆

Direct Thermal 200WS FSC

An FSC® certified, smooth, white matte paper with a barrier coated thermosensitive layer suitable.

- Suitable for general purpose barcode labeling for retail and weight scale printing with medium to low speed barcode thermal printing.
- Thinner and lighter facestock with added conformability

Basis Weight	67 g/m ²
Thickness	70 µm
Print Definition	★★★★★
Print Durability	★★☆

Direct Thermal 200ST FSC

An FSC® certified, white woodfree paper with a barrier-coated thermo-sensitive layer.

- Designed with essential resistance and suitable for barcode labeling in dry environment for logistic, ship and track printing with medium to low speed barcode thermal printing.
- Thinner and lighter facestock with added conformability

Basis Weight	65 g/m ²
Thickness	70 µm
Print Definition	★★★★★
Print Durability	★★☆

Direct Thermal 60 TC FSC

An FSC® certified, white woodfree paper with a barrier-coated thermo-sensitive layer.

- Designed with essential resistance and suitable for barcode labeling in dry environment for logistic, ship and track printing with medium to low speed barcode thermal printing.
- Thinner and lighter facestock with added conformability

Basis Weight	60 g/m ²
Thickness	60 µm
Print Definition	★★★★★
Print Durability	★★☆



Facestock / VI Paper (continued)

Direct Thermal (continued)

Direct Thermal 150RL FSC

An FSC® certified, white woodfree paper with a barrier-coated thermo-sensitive layer.

- Moderate print quality for barcode labelling where the environment is dry and label life cycle is short
- Suitable for applications such as weighing scale, dry pre-packed food (deli, nuts, etc), e-commerce, ship & track for short distance.

Basis Weight	73 g/m ²
Thickness	74 µm
Print Definition	★★★
Print Durability	★★

rDirect Thermal 300LD FSC

An FSC® certified, smooth, white woodfree paper with a thermo-sensitive layer, consists of 15% recycled content.

- The recycled DT paper contains 15% recycled content, making this is a more sustainable label option, helping brands achieve higher recycled content in the packaging.
- Designed for barcode labelling where the environment is dry and the label life cycle is short e.g. warehouse logistics
- labelling, address labelling, and dry retails barcode labelling.
- Suitable for barcode labelling with less demanding on image durability.

Basis Weight	70 g/m ²
Thickness	75 µm
Print Definition	★★☆
Print Durability	★☆

Baggage Tag FSC

An FSC® certified, smooth, white woodfree paper with a barrier coated thermosensitive layer.

- Laminated with special BOPP film featuring very good tear resistance.
- Ideal application is labels for airport baggage tag thermal printing system with good print quality and definition.
- The ink receptive and protective layer features very good resistance to moisture, abrasion, etc., which the baggage tag might contact to during transportation.

Basis Weight	121 g/m ²
Thickness	124 µm

Baggage Tag Elite FSC

An FSC® certified, white woodfree paper with a barrier-coated thermo-sensitive layer

- Good tear resistance with heat sensitive paper is laminated with special BOPP film
- Designed for airport baggage tag thermal printing systems with moderate to good print quality and definition.
- The ink receptive and protective layer features essential resistance to moisture, abrasion, etc., which the baggage tag might contact to during transportation

Basis Weight	114 g/m ²
Thickness	118 µm



Facestock / VI Paper (continued)

Thermal Transfer

Trantherm 2C FSC

An FSC® certified, bright white, ultra-smooth coated facestock.

- Designed for high quality barcode printing. Compatibility with a wide range of wax and wax-resin thermal transfer ribbons.
- Offers excellent smudge resistance.
- Applications include address, identification, tracking, and shipping labels for offices, industrial as well as retail.

Basis Weight	81 g/m ²
Thickness	89 µm
Print Definition	★★★★★
Print Durability	★★★★★

Trantherm Plus FSC

An FSC® certified, bright matte white, pigmented woodfree printing paper.

- Designed for use in thermal transfer printers running at slow to high speed.
- Good print resolution with good smudge resistance.
- Applications include address, identification, tracking, and shipping labels for offices, industrial and retail.

Basis Weight	62 g/m ²
Thickness	66 µm
Print Definition	★★★★
Print Durability	★★★★

TT Elite FSC

An FSC® certified, bright matte white, woodfree coated paper.

- Designed for use in thermal transfer printers running at slow to high speed.
- Good print resolution with good smudge resistance.
- Applications include address, identification, tracking, and shipping labels for offices, industrial and retail.

Basis Weight	62 g/m ²
Thickness	60 µm

Laser/Inkjet Paper

LCJ Premium FSC

An FSC® certified, matte white, woodfree, machine finished paper with good opacity, excellent absorption and superior toner bonding characteristics

- Designed for the manufacture of A4 sheets for use in laser printers, copiers and monochrome inkjet printer.
- The facestock's surface structure provides excellent toner bonding and print resolution.
- Ideal for label applications using variable information such as address, instruction and inventory labels, labels for office use and many other applications.

Basis Weight	64 g/m ²
Thickness	74 µm



Facestock / VI Film

Direct Thermal

Baggage Tag 300BA

A direct thermal opaque white polypropylene film, coated with thermal sensitive material formulation

- Excellent tear resistance and durability during baggage handling at airport.
- Offers excellent print quality and definition.
- Ink receptive and protective layer features very good resistance to moisture, abrasion, etc., which the baggage tag might contact to during transportation.

Basis Weight 70 g/m²

Thickness 85 µm

Direct Thermal PP 300BL

A white BOPP film with a barrier-coated thermosensitive layer.

- Designed for high speed barcode thermal printing with good print definition
- Offers excellent facestock durability, with added conformability.
- Suitable for barcode labelling where excellent resistance to moisture, oils and fats is required in the retail and industrial sectors e.g. pre-packed food, meat and fish, laboratory items and pharmaceutical applications.
- Additional durability including smudge and moisture resistance is required.

Basis Weight 70 g/m²

Thickness 85 µm



Facestock / Specialty Paper

Foil

Matte Silver Foil FSC

- A top coated aluminium foil, laminated to a white woodfree printing paper, with a matte silver finish
- Designed to provide metalized appearance which is ideal for primary labeling of premium goods such as cosmetics, household goods, toiletries or promotional labels.
- Typical applications include labels for cosmetic, food products and promotional labels.

Basis Weight 80 g/m²

Thickness 65 µm

Bright Silver Foil FSC

- A top coated aluminium foil, laminated to a white woodfree printing paper, with a bright silver finish.
- Provide metalized appearance which is ideal for primary labeling of premium good such as cosmetics, household goods, toiletries or promotional labelss

Basis Weight 80 g/m²

Thickness 65 µm

Radiants

Radiants Range FSC

- A one side fluorescent coated, woodfree printing paper, available in yellow, orange, red, pink, green
- Designed for applications requiring fluorescent colors to distinguish products.
- General purpose labels for eye-catching applications such as warning, instruction, promotional, advertising labels and price marking.
- Available in various colours to cater for specific needs.

Basis Weight 78 g/m²

Thickness 73 µm



Facestock / Specialty Paper (continued)

Wine – Uncoated Paper

Vintage FSC

- A white uncoated paper facestock featuring wet strength properties and a new generation coating that provides higher opacity in wet conditions and higher resistance to moisture.
- Primary labeling of wine and premium beverage.
- Delivers good scuff resistance and environmental resistance, Ä when offered with a suitable varnish.
- Where sharp multi-colour work is required. Where high gloss levels are required.

Basis Weight	110 g/m ²
Thickness	130 µm

Estate #4 PE FSC

- A white vellum uncoated paper facestock featuring wet strength properties and a new generation extruded film under-laminate.
- Primary labeling of wine, beverage and specialist foods.
- Polymer layer greatly improves moisture barrier properties.
- Polymer layer reduces the severity of paper fiber swelling induced “bubbling” on difficult substrates.

Basis Weight	109 g/m ²
Thickness	139 µm

Estate #8 PE FSC

- An FSC certified, white vellum uncoated paper facestock featuring wet strength properties and a new generation extruded film under-laminate.
- Primary labeling of wine, beverage and specialist foods.
- Polymer layer greatly improves moisture barrier properties.
- Polymer layer reduces the severity of paper fiber swelling induced “bubbling” on difficult substrates.

Basis Weight	114 g/m ²
Thickness	140 µm

Artisan Plus FSC

- A white, uncoated matt woodfree printing paper, under-laminated with a felt marked finish, giving the paper a tactile “hand-made” appearance and feel. Wet strength and fungicidal treatment.

Basis Weight	136 g/m ²
Thickness	165 µm

KW Gen 3 PE FSC

- Bright white, smooth uncoated wet strength paper with a custom PE underlamine. offering a white appearance ideal for wine and high end beverages.

Basis Weight	120 g/m ²
Thickness	135 µm



Facestock / Specialty Film

Polypropylene (PP) – White

PP40 Top Matte White

A bi-axially oriented matte white polypropylene film with a print-receptive top coating. The metalized coating is applied to the non-printing side of the film for better block-out feature.

- Ideal for daily, food and household product packaging.
- Ideal for applications requiring 'substrate identical labeling' on polypropylene containers and in environmentally sensitive markets requiring recycling of 'polyolefin' packs.
- Due to fairly rigid nature of polypropylene, care should be taken with the use on 'non-uniform' surfaces or where a high level of squeezability is desired.

Basis Weight	28 g/m ²
Thickness	38 µm

Synthetic Paper

Synthetic Paper TR75

- A matte white, high opacity polypropylene film which is suitable for flexographic, letterpress, screen & thermal transfer printing and has high strength and durability as well as good moisture and chemical resistance.
- Gives printing performance in thermal transfer printing as well as conventional printing techniques.
- Can be printed well with flexographic and letterpress.
- Can also be printed with thermal transfer when matched with the correct ribbon.

Basis Weight	59 g/m ²
Thickness	75 µm
Printability	★★★★★
Stiffness	★★★★☆
Conformability	★★

Synthetic Paper II

- A bi-axially oriented, matte white polypropylene film with a print receptive top coating.
- Gives excellent printing performance in thermal transfer printing when matched with the correct ribbon as well as conventional printing techniques including flexographic, letterpress, and screen printing techniques.
- Applications include labeling of quality products such as cosmetics, toiletries, luxury articles and promotional labeling as well as automotive lubricants and household chemicals, whereby durability and resistance to moisture as well as variable information printing are required.
- Due to semi-rigid nature of polypropylene, care should be taken with 'non-uniform' surfaces or highly squeezable applications.

Basis Weight	62 g/m ²
Thickness	78 µm
Printability	★★★★☆
Stiffness	★★★★★
Conformability	★★



Facestock / Specialty Film (continued)

Synthetic Paper (continued)

3 Mil Synthetic Paper

- A bi-axially oriented, matte white polypropylene film with a print receptive top coating, which is suitable for conventional and thermal transfer printing, with good durability.
- Gives excellent printing performance in thermal transfer printing as well as conventional printing techniques.
- Can be printed well with flexographic, letterpress and screen printing techniques.
- Can also be printed with thermal transfer when matched with the correct ribbon.
- Therefore, careful selection of ribbon and preliminary testing is essential. In case solvent screen inks are used, please consult your ink manufacturer.

Basis Weight	59 g/m ²
Thickness	75 µm
Printability	★★★★
Stiffness	★★★☆☆
Conformability	★★

rSynthetic Paper

A matt white polypropylene cavitated film with a print-receptive top coating.

- The recycled PP film 30% post-industrial waste (PIW) recycled content, making this a more sustainable label option, helping brands achieve higher recycled content in the packaging.
- Excellent printing performance in thermal transfer printing when matched with the correct ribbon as well as conventional printing techniques including flexographic, letterpress, and screen printing techniques.

Basis Weight	49 g/m ²
Thickness	70 µm

WBIJ Synthetic Paper

A matte white inkjet synthetic paper material with a highly absorbent surface structure specifically designed for water based inkjet printing approach (WBIJ)

- An ideal choice for printing labels by on-demand-color inkjet printers where full process color is used to add impact and/or functionality to the label. The high ink holdout and quick drying provide for excellent clarity and density of printed graphics, making it the perfect choice for primary and secondary packaging labels in retail, manufacturing, health care, and logistics etc.

Basis Weight	68 g/m ²
Thickness	97 µm



Facestock / Specialty Film (continued)

Polypropylene (PP) - White

WBIJ PP Top Gloss White

A gloss white inkjet polypropylene film material with a highly absorbent surface structure specifically designed for water based inkjet printing approach (WBIJ).

- An ideal choice for printing labels by on-demand-color inkjet printers where full process color is used to add impact and/or functionality to the label. The high ink holdout and quick drying provide for excellent clarity and density of printed graphics, making it the perfect choice for primary and secondary packaging labels in retail, manufacturing, health care, and logistics etc.

Basis Weight	70 g/m ²
Thickness	85 µm

Polyester (PET) - Clear

1M Clear PET TC

A top coated, glossy and highly transparent overlaminating film

- Featuring excellent tear strength, heat resistance, dimensional stability and chemical resistance.

Basis Weight	33 g/m ²
Thickness	25 µm
Printability	★★★★★
Stiffness	★★★
Conformability	-

PET Top Clear

A clear polyester facestock with a print-receptive top coating.

- Features product features excellent tear strength, heat resistance, dimensional stability, opacity and chemical resistance. Designed for conventional printing techniques. Specially formulated inks are normally not necessary. It is however also suitable for thermal transfer printing. Ink/ribbon testing is always recommended before production. Suitable for use in a Pop-Up labeling applications.

Basis Weight	72 g/m ²
Thickness	50 µm



Facestock / Durables Film

Polyester (PET) - White

2M White PET TC

A homogeneously pigmented white facestock featuring excellent tear strength, heat resistance, dimensional stability, opacity and chemical resistance.

- Designed for printing with most solvent, UV cured and some water-based flexographic inks.
- Suitable for thermal transfer printing applications with select thermal transfer ribbons. Specific testing is required.

Basis Weight	76 g/m ²
Thickness	50 µm
Printability	★★★★★
Stiffness	★★★★
Conformability	-

75µm Matte White PET TC

A matte white polyester facestock with a smooth, absorbent ink-receptive top coating.

- Features excellent tear strength, heat resistance, dimensional stability, opacity and chemical resistance.
- Suitable for use in a wide range of durable labeling applications.

Basis Weight	84 g/m ²
Thickness	75 µm
Printability	★★★★
Stiffness	★★★★★
Conformability	-

50µm Matte White PET TC

A matte white polyester facestock with a smooth, absorbent ink-receptive top coating.

- Features excellent tear strength, heat resistance, dimensional stability, opacity and chemical resistance.
- Suitable for use in a wide range of durable labeling applications.

Basis Weight	60 g/m ²
Thickness	50 µm
Printability	★★★★
Stiffness	★★★★
Conformability	-



Facestock / Durables Film (continued)

Polyester (PET) - Metalized

50µm Bright Silver PET TC

A bright metallic polyester facestock with a smooth, absorbent ink-receptive top coating.

- Suitable for a wide range of promotional labels.
- Features excellent tear strength, heat resistance, dimensional stability, opacity and chemical resistance.

Basis Weight	71 g/m ²
Thickness	50 µm
Printability	★★★★★
Stiffness	★★★★★
Conformability	-

2M Matte Ch PET TC

A matte finished metallic film featuring excellent tear strength, heat resistance, dimensional stability, opacity and chemical resistance.

- Designed for printing with most solvent, UV cured and some water-based flexographic inks.
- Suitable for thermal transfer printing applications with select thermal transfer ribbons.

Basis Weight	72 g/m ²
Thickness	50 µm
Printability	★★★★★
Stiffness	★★★★★
Conformability	-

1M Matte Ch PET TC

A matte finished metallic, top coated polyester film featuring excellent tear strength, heat resistance, dimensional stability, opacity and chemical resistance.

- Designed for printing with most solvent UV cured and some water-based flexographic inks.
- Suitable for thermal transfer printing applications with select thermal transfer ribbons.

Basis Weight	35 g/m ²
Thickness	25 µm
Printability	★★★★★
Stiffness	★★★
Conformability	-

Copy Code CH PET Plus

A matte finished metallic film featuring excellent tear strength, heat resistance, dimensional stability, opacity and chemical resistance.

- Designed for printing with most solvent, UV cured and some water-based flexographic inks.
- Suitable for use in a wide range of durable labeling applications whereby UL recognition is required.

Basis Weight	75 g/m ²
Thickness	58 µm
Printability	★★★
Stiffness	★★★★★
Conformability	-

Polyester (PETC) - White

2M WH PETC TC

A semi-gloss finished white polyester film with a smooth, absorbent ink-receptive top coating.

- Designed for printing with most solvent UV cured and some water-based flexographic inks.
- Suitable for thermal transfer printing applications with select thermal transfer ribbons.

Basis Weight	71 g/m ²
Thickness	50 µm
Printability	★★★★★
Stiffness	★★★☆☆
Conformability	-



Adhesives



Adhesive comparison table

General Purpose - Papers

General Purpose - Papers						Application							Substrates					Indirect Food	
						Freezer	Chilled	Wet Surfaces	Tight Mandrel	Ice Bucket	Durable	Removable	Cardboard	Glass	PET	HDPE	LDPE		PP
						Initial Tack	Ultimate Adhesion	Min. App. Temp.	Service Temp.										
Permanent																			
S1002	Emulsion Acrylic	*	*	5°C	-20°C to 80°C									✓	✓	✓		✓	✓
S1005	Emulsion Acrylic	**	**	5°C	-20°C to 80°C									✓	✓	✓		✓	✓
S1010	Emulsion Acrylic	***	***	5°C	-20°C to 80°C									✓	✓	✓		✓	✓
M3000	Emulsion Acrylic	***	***	5°C	-20°C to 80°C									✓	✓	✓		✓	✓
M3300	Emulsion Acrylic	***	***	5°C	-20°C to 80°C									✓	✓	✓		✓	✓
S2492	Emulsion Acrylic	***	***	5°C	-20°C to 80°C									✓	✓	✓		✓	✓
S2090	Emulsion Acrylic	****	****	5°C	-20°C to 80°C					✓			✓	✓	✓	✓		✓	✓
S2420	Emulsion Acrylic	*****	*****	5°C	-20°C to 80°C					✓			✓	✓	✓	✓	✓	✓	✓
S2010N	Rubber-based Hotmelt	*****	***	0°C	-40°C to 70°C					✓			✓	✓	✓	✓	✓	✓	✓
S2025N	Rubber-based Hotmelt	*****	****	0°C	-40°C to 70°C					✓			✓	✓	✓	✓	✓	✓	✓
Removable																			
R423	Emulsion Acrylic	Medium	Medium	-12°C	-40°C to 70°C							✓	✓			✓	✓	✓	✓
R450	Emulsion Acrylic	Medium	Medium	-15°C	-30°C to 70°C							✓	✓			✓	✓	✓	✓

General Purpose - Films

General Purpose - Films						Application							Substrates					Indirect Food	
						Freezer	Chilled	Wet Surfaces	Tight Mandrel	Ice Bucket	Durable	Removable	Cardboard	Glass	PET	HDPE	LDPE		PP
		Initial Tack	Ultimate Adhesion	Min. App. Temp.	Service Temp.														
Permanent																			
S6800	Emulsion Acrylic	Medium	High	5°C	-20°C to 80°C									✓	✓			✓	✓
S692N	Emulsion Acrylic	High	High	5°C	-20°C to 80°C				✓					✓	✓	✓	✓	✓	✓
S4700N	Emulsion Acrylic	High	High	5°C	-20°C to 80°C						✓				✓	✓		✓	✓
S3000	Emulsion Acrylic	High	Very High	5°C	-20°C to 80°C				✓					✓	✓	✓	✓	✓	✓
S3010N	Rubber-based Hotmelt	Very High	High	5°C	-40°C to 70°C				✓				✓	✓	✓	✓	✓	✓	✓
Removable																			
R480	Emulsion Acrylic	Medium	Medium	-15°C	-30°C to 70°C							✓	✓			✓	✓	✓	✓



Special Purpose

Special Purpose						Application							Substrates						Indirect Food						
						Freezer	Chilled	Wet Surfaces	Tight Mandrel	Ice Bucket	Durable	Removable	Cardboard	Glass	PET	HDPE	LDPE	PP							
Initial Tack						Ultimate Adhesion		Min. App. Temp.		Service Temp.															
Permanent																									
S631	Emulsion Acrylic	High	High	5°C	-20°C to 80°C				✓					✓	✓	✓	✓	✓	✓						
S7200	Emulsion Acrylic	Medium	Medium	5°C	-40°C to 80°C																				
SR3013	Emulsion Acrylic	High	High	5°C	-20°C to 80°C									✓	✓	✓	✓	✓	✓						
C7501	Emulsion Acrylic	Medium	Medium	-40°C	-50°C to 90°C		✓							✓	✓	✓	✓	✓	✓						
S2800	Emulsion Acrylic	Medium	Medium	-15°C	-50°C to 80°C	✓	✓							✓	✓	✓	✓	✓							
C2075	Rubber-based Hotmelt	High	High	-20°C	-50°C to 70°C	✓		✓		✓				✓	✓	✓	✓	✓	✓						
C2076	Rubber-based Hotmelt	High	High	-10°C	-40°C to 70°C	✓	✓	✓						✓	✓	✓	✓	✓	✓						
C2076C	Rubber-based Hotmelt	High	Medium	0°C	-40°C to 70°C		✓	✓						✓	✓	✓	✓	✓	✓						
S333	Emulsion Acrylic	High	High	-4°C	-40°C to 145°C						✓			✓	✓	✓		✓							
S369	Emulsion Acrylic	Medium	High	-4°C	-40°C to 145°C						✓			✓	✓	✓		✓							
S8020	Emulsion Acrylic	Medium	Medium	5°C	-20°C to 80°C						✓				✓	✓		✓	✓						
S2060	Rubber-based Hotmelt	High	Very High	0°C	-40°C to 70°C						✓			✓	✓	✓		✓	✓						
S2059	Rubber-based Hotmelt	Very High	Very High	5°C	-40°C to 70°C				✓					✓	✓	✓	✓	✓	✓						
TS79	Rubber-based Hotmelt	Very High	Very High	0°C	-40°C to 70°C						✓			✓		✓	✓	✓	✓						
WLP	Emulsion Acrylic	High	High	5°C	-20 °C to 70°C		✓			✓				✓	✓	✓		✓	✓						
WLK202	Emulsion Acrylic	Very High	Very High	-5°C	-30°C to 70°C		✓	✓	✓	✓				✓	✓	✓	✓	✓	✓						
S2030	Emulsion Acrylic	Very High	Very High	5°C	-20°C to 80°C		✓			✓				✓	✓				✓						
Z3338N	Emulsion Acrylic	High	High	-20°C	-50°C to 80°C		✓	✓	✓	✓				✓	✓	✓	✓	✓	✓						
S477A	Emulsion Acrylic	High	High	5°C	-20°C to 80°C									✓	✓	✓	✓	✓							
Removable																									
Z3000	Rubber-based Hotmelt	High	Medium	-4°C	-50°C to 70°C		✓					✓													



Adhesive / General Purpose / Papers

Permanent

S1002

Emulsion Acrylic

A general purpose permanent acrylic based adhesive suitable for paper reels

- Good adhesion to high surface energy substrates.
- Exhibits low bleed characteristics.
- Good diecutting and stripping properties.

Initial tack	*
Ultimate adhesion	*
Minimum application temperature	5°C
Service temperature	-20°C to 80°C
Indirect Food	✓
Application	Substrates
Freezer	Cardboard
Chilled	✓ Glass
Wet Surfaces	✓ PET
Tight mandrel	✓ HDPE
Ice bucket	LDPE
Durable	✓ PP
Removable	

S1005

Emulsion Acrylic

A general purpose permanent acrylic based adhesive suitable for paper reels

- Good initial tack and adhesion on a variety of substrates.
- Exhibits low bleed characteristics
- Good diecutting & guillotining properties.

Initial tack	**
Ultimate adhesion	**
Minimum application temperature	5°C
Service temperature	-20°C to 80°C
Indirect Food	✓
Application	Substrates
Freezer	Cardboard
Chilled	✓ Glass
Wet Surfaces	✓ PET
Tight mandrel	✓ HDPE
Ice bucket	LDPE
Durable	✓ PP
Removable	

S1010

Emulsion Acrylic

A general purpose permanent acrylic based adhesive for paper reels

- Excellent initial tack and adhesion on a variety of substrates.
- Exhibits low bleed characteristics.
- Good diecutting & guillotining properties.
- Demonstrates good UV resistance and aged performance.

Initial tack	***
Ultimate adhesion	***
Minimum application temperature	5°C
Service temperature	-20°C to 80°C
Indirect Food	✓
Application	Substrates
Freezer	Cardboard
Chilled	✓ Glass
Wet Surfaces	✓ PET
Tight mandrel	✓ HDPE
Ice bucket	LDPE
Durable	✓ PP
Removable	



Adhesive / General Purpose / Papers (continued)

Permanent (continued)

M3000

Emulsion Acrylic

A general purpose permanent acrylic based adhesive for paper reels

- Provides optimum “price-performance” factor suitable for mid-high surface energy substrates.
- Recommended for paper products with kraft liner.

Initial tack	***
Ultimate adhesion	***
Minimum application temperature	5°C
Service temperature	-20°C to 80°C
Indirect Food	✓
Application	Substrates
Freezer	Cardboard
Chilled	✓ Glass
Wet Surfaces	✓ PET
Tight mandrel	✓ HDPE
Ice bucket	LDPE
Durable	✓ PP
Removable	

M3300

Emulsion Acrylic

A general purpose permanent acrylic based adhesive for paper reels

- Provides optimum “price-performance” factor suitable for mid-high surface energy substrates.

Initial tack	***
Ultimate adhesion	***
Minimum application temperature	5°C
Service temperature	-20°C to 80°C
Indirect Food	✓
Application	Substrates
Freezer	Cardboard
Chilled	✓ Glass
Wet Surfaces	✓ PET
Tight mandrel	✓ HDPE
Ice bucket	LDPE
Durable	✓ PP
Removable	

S2492

Emulsion Acrylic

A general purpose permanent acrylic based adhesive

- Featuring high cohesive strength, which is necessary for LCJ applications
- Designed to give good adhesion to plastic and paper substrates on which the mailing address label is applied.

Initial tack	***
Ultimate adhesion	***
Minimum application temperature	5°C
Service temperature	-20°C to 80°C
Indirect Food	✓
Application	Substrates
Freezer	Cardboard
Chilled	✓ Glass
Wet Surfaces	✓ PET
Tight mandrel	✓ HDPE
Ice bucket	LDPE
Durable	✓ PP
Removable	



Adhesive / General Purpose / Papers (continued)

Permanent (continued)

S2090

Emulsion Acrylic

A general purpose permanent acrylic based adhesive suitable for paper reels

- High initial tack with excellent adhesion properties.
- Good diecutting and stripping properties.
- Excellent adhesion to a wide range of substrates, e.g. HDPE, recycled corrugated cardboard and difficult substrates.
- Suitable for use on rough surfaces, such as recycled board.

Initial tack	****
Ultimate adhesion	****
Minimum application temperature	5°C
Service temperature	-20°C to 80°C
Indirect Food	✓
Application	Substrates
Freezer	✓ Cardboard
Chilled	✓ Glass
Wet Surfaces	✓ PET
✓ Tight mandrel	✓ HDPE
Ice bucket	LDPE
Durable	✓ PP
Removable	

S2420

Emulsion Acrylic

A general purpose permanent acrylic based adhesive suitable for paper reels

- Featuring ultra-high initial tack with excellent adhesion properties on a wide range of substrates.
- Suitable for low surface energy or textured substrates like HDPE or PP and textured substrates like carton box.

Initial tack	*****
Ultimate adhesion	*****
Minimum application temperature	5°C
Service temperature	-20°C to 80°C
Indirect Food	✓
Application	Substrates
Freezer	✓ Cardboard
Chilled	✓ Glass
Wet Surfaces	✓ PET
✓ Tight mandrel	✓ HDPE
Ice bucket	✓ LDPE
Durable	✓ PP
Removable	

S2010N

Rubber-based Hotmelt

A general purpose permanent hotmelt adhesive with high tack and good adhesion, enabling enhanced converting performance

- High tack and good adhesion on a wide variety of substrates, including apolar, slightly rough and curved substrates.
- Improve convertibility by enabling higher die-cutting speed.
- Good die-cutting & stripping properties

Initial tack	*****
Ultimate adhesion	***
Minimum application temperature	0°C
Service temperature	-40°C to 70°C
Indirect Food	✓
Application	Substrates
Freezer	✓ Cardboard
Chilled	✓ Glass
Wet Surfaces	✓ PET
✓ Tight mandrel	✓ HDPE
Ice bucket	✓ LDPE
Durable	✓ PP
Removable	



Adhesive / General Purpose / Papers (continued)

Permanent (continued)

S2025N Rubber-based Hotmelt

A general purpose permanent hotmelt adhesive with superior tack and adhesion.

- Excellent tack and adhesion on a wide variety of substrates, including apolar, slightly rough and curved substrates.
- This adhesive is designed specifically for application at room temperature onto cardboard substrates.
- Developed to facilitate conversion speed - similar to acrylic emulsion adhesives

Initial tack	*****
Ultimate adhesion	****
Minimum application temperature	0°C
Service temperature	-40°C to 70°C
Indirect Food	✓
Application	Substrates
Freezer	✓ Cardboard
Chilled	✓ Glass
Wet Surfaces	✓ PET
✓ Tight mandrel	✓ HDPE
Ice bucket	✓ LDPE
Durable	✓ PP
Removable	



Adhesive / General Purpose / Papers (continued)

Removable

R423 Emulsion Acrylic

A removable adhesive featuring long term removability and excellent die-cutting and stripping characteristics

- Featuring clean removability on a wide range of substrates over long periods of time depending on several factors i.e. type and shape of substrate, temperature, exposure to UV light, etc.
- preliminary testing is essential prior using

Initial tack	Medium
Ultimate adhesion	Medium
Minimum application temperature	-12°C
Service temperature	-40°C to 70°C
Indirect Food	✓
Application	Substrates
Freezer	✓ Cardboard
Chilled	Glass
Wet Surfaces	PET
Tight mandrel	✓ HDPE
Ice bucket	✓ LDPE
Durable	✓ PP
✓ Removable	

R450 Emulsion Acrylic

A removable adhesive featuring excellent long term removability

- Featuring excellent removability on a wide range of substrates over a period of time depending on type of substrates.
- Therefore, preliminary testing is essential prior using the product.

Initial tack	Medium
Ultimate adhesion	Medium
Minimum application temperature	-15°C
Service temperature	-30°C to 70°C
Indirect Food	✓
Application	Substrates
Freezer	✓ Cardboard
Chilled	Glass
Wet Surfaces	PET
Tight mandrel	✓ HDPE
Ice bucket	✓ LDPE
Durable	✓ PP
✓ Removable	



Adhesive / General Purpose / Films

Permanent

S6800

Emulsion Acrylic

A general purpose permanent, emulsion acrylic adhesive for films

- Specially formulated to provide excellent clarity on clear filmic facestocks.

Initial tack	Medium
Ultimate adhesion	High
Minimum application temperature	5°C
Service temperature	-20°C to 80°C
Indirect Food	✓
Application	Substrates
Freezer	Cardboard
Chilled	✓ Glass
Wet Surfaces	✓ PET
Tight mandrel	HDPE
Ice bucket	LDPE
Durable	✓ PP
Removable	

S692N

Emulsion Acrylic

A general purpose permanent acrylic based adhesive designed for filmic facestocks

- High degree of clarity and “wet out” for clear filmic facestocks
- Good initial tack and adhesion on a variety of substrates including apolar surfaces
- Exhibits low bleed characteristics
- Good die-cutting and stripping properties
- Offers a wide service temperature range
- Demonstrates good UV resistance
- Limited resistance to plasticisers found in PVC substrates and low molecular weight oils

Initial tack	High
Ultimate adhesion	High
Minimum application temperature	5°C
Service temperature	-20°C to 80°C
Indirect Food	✓
Application	Substrates
Freezer	Cardboard
Chilled	✓ Glass
Wet Surfaces	✓ PET
✓ Tight mandrel	✓ HDPE
Ice bucket	✓ LDPE
Durable	✓ PP
Removable	

S4700N

Emulsion Acrylic

A general purpose permanent, emulsion acrylic adhesive for films

- Predominantly use in cosmetics, toiletries and luxury items
- Also used for promotional labelling, as well as lubricant and household chemical labels where durability and resistance to moisture is required

Initial tack	High
Ultimate adhesion	High
Minimum application temperature	5°C
Service temperature	-20°C to 80°C
Indirect Food	✓
Application	Substrates
Freezer	Cardboard
Chilled	Glass
Wet Surfaces	✓ PET
Tight mandrel	✓ HDPE
Ice bucket	LDPE
✓ Durable	✓ PP
Removable	



Adhesive / General Purpose / Films (continued)

Permanent (continued)

S3000

Emulsion Acrylic

a general purpose permanent, clear acrylic based adhesive

- Designed for prime labeling
- Suitable for squeezable and clear facestock applications
- Exhibit low ooze and high temperature resistance properties
- Designed to give balanced performance between good clarity and excellent resistance to various liquids

Initial tack	High
Ultimate adhesion	Very High
Minimum application temperature	5°C
Service temperature	-20°C to 80°C
Indirect Food	✓
Application	Substrates
Freezer	Cardboard
Chilled	✓ Glass
Wet Surfaces	✓ PET
✓ Tight mandrel	✓ HDPE
Ice bucket	✓ LDPE
Durable	✓ PP
Removable	

S3010N

Rubber-based Hotmelt

A general purpose permanent hotmelt adhesive with high tack and good adhesion, enabling enhanced converting performance

- High tack and good adhesion on a wide variety of substrates, including apolar, slightly rough and curved substrates.
- Improve convertibility by enabling higher die-cutting speed.
- Good die-cutting & stripping properties

Initial tack	Very High
Ultimate adhesion	High
Minimum application temperature	5°C
Service temperature	-40°C to 70°C
Indirect Food	✓
Application	Substrates
Freezer	✓ Cardboard
Chilled	✓ Glass
Wet Surfaces	✓ PET
✓ Tight mandrel	✓ HDPE
Ice bucket	✓ LDPE
Durable	✓ PP
Removable	



Adhesive / General Purpose / Films (continued)

Removable

R480 Emulsion Acrylic

A removable adhesive featuring long term removability and excellent die-cutting and stripping characteristics

- Featuring excellent removability on a wide range of substrates over a period of time depending on type of substrates.
- Therefore, preliminary testing is essential prior using the product.

Initial tack	Medium
Ultimate adhesion	Medium
Minimum application temperature	-15°C
Service temperature	-30°C to 70°C
Indirect Food	✓
Application	Substrates
Freezer	✓ Cardboard
Chilled	Glass
Wet Surfaces	PET
Tight mandrel	✓ HDPE
Ice bucket	✓ LDPE
Durable	✓ PP
✓ Removable	



Adhesive / Special Purpose

Permanent

S631

Emulsion Acrylic

A dedicated adhesive suitable for beverage application

- Designed specifically to address beverage market application needs.
- Actual application test is necessary to determine the suitability of use.

Initial tack	High
Ultimate adhesion	High
Minimum application temperature	5°C
Service temperature	-20°C to 80°C
Indirect Food	✓
Application	Substrates
Freezer	Cardboard
Chilled	✓ Glass
Wet Surfaces	✓ PET
✓ Tight mandrel	✓ HDPE
Ice bucket	✓ LDPE
Durable	✓ PP
Removable	

S7200

Emulsion Acrylic

A clear permanent acrylic adhesive designed specifically for beer label applications which require resistance to water.

- Engineered to be applied to moist surfaces typically found in brewery (beer) applications.
- Maintains clarity through exposure to extended exposure to ice water (72 hours).
- This adhesive has excellent wetout, converting, stripping, and dispensing characteristics.

Initial tack	Medium
Ultimate adhesion	Medium
Minimum application temperature	5°C
Service temperature	-40°C to 80°C
Indirect Food	
Application	Substrates
Freezer	Cardboard
Chilled	Glass
Wet Surfaces	PET
Tight mandrel	HDPE
Ice bucket	LDPE
Durable	PP
Removable	

SR3013

Emulsion Acrylic

A dedicated adhesive suitable for recycling of PET bottles and PET containers

- Designed specifically for labeling and recycling of PET bottles and PET containers
- Excellent clarity and “wet out” for clear filmic facestocks
- Strong adhesion to PET containers until the very end of its life cycle, when in the sink/float process at the recycler the adhesive is deactivated in a caustic bath, allowing the facestock and adhesive to cleanly separate from the PET flakes. No residual adhesive remains on the rPET flakes

Initial tack	High
Ultimate adhesion	High
Minimum application temperature	5°C
Service temperature	-20°C to 80°C
Indirect Food	✓
Application	Substrates
Freezer	Cardboard
Chilled	✓ Glass
Wet Surfaces	✓ PET
Tight mandrel	✓ HDPE
Ice bucket	✓ LDPE
Durable	✓ PP
Removable	



Adhesive / Special Purpose (continued)

Permanent (continued)

C7501

Emulsion Acrylic

A permanent, emulsion acrylic adhesive featuring excellent cold temperature performance.

- Provide good room temperature performance and excellent cold temperature performance without sacrificing good die-cutting and stripping properties.
- Features good tack and adhesion to a wide variety of packaging materials, such as paper, cardboard and films.
- Ideally suitable for labeling applications whereby application temperature is below freezing point e.g. labeling of chilled products.

Initial tack	Medium
Ultimate adhesion	Medium
Minimum application temperature	-40°C
Service temperature	-50°C to 90°C
Indirect Food	✓
Application	Substrates
Freezer	✓ Cardboard
✓ Chilled	✓ Glass
Wet Surfaces	✓ PET
Tight mandrel	✓ HDPE
Ice bucket	✓ LDPE
Durable	✓ PP
Removable	

S2800

Emulsion Acrylic

A special purpose permanent, acrylic based adhesive for direct food contact.

- Direct food contact. complies with European food regulation 1935/2004/EC.
- A special purpose permanent, acrylic based adhesive for direct food contact is developed to provide good room temperature performance and excellent cold temperature.
- S2800 is approved for direct food contact onto moist and fatty foods.
- Typical applications include labels for food packaging and applications where contact with oils and greases are expected.
- Designed for labelling cheese rinds on large cheeses and carcass labelling
- A broad range of specialist adhesives and constructions

Initial tack	Medium
Ultimate adhesion	Medium
Minimum application temperature	-15°C
Service temperature	-50°C to 80°C
Indirect Food	
Application	Substrates
✓ Freezer	Cardboard
✓ Chilled	✓ Glass
Wet Surfaces	✓ PET
Tight mandrel	✓ HDPE
Ice bucket	✓ LDPE
Durable	✓ PP
Removable	

C2075

Rubber-based Hotmelt

A global rubber based freezer grade permanent adhesive.

- Excellent cold temperature performance but moderate room temperature performance.
- Good adhesion performance can be achieved on slightly frosted surfaces.
- Resistant to moisture during thawing.
- Suitable for a wide variety of packaging materials and in particular flexible films

Initial tack	High
Ultimate adhesion	High
Minimum application temperature	-20°C
Service temperature	-50°C to 70°C
Indirect Food	✓
Application	Substrates
✓ Freezer	✓ Cardboard
Chilled	✓ Glass
✓ Wet Surfaces	✓ PET
Tight mandrel	✓ HDPE
✓ Ice bucket	✓ LDPE
Durable	✓ PP
Removable	



Adhesive / Special Purpose (continued)

Permanent (continued)

C2076

Rubber-based Hotmelt

A rubber based, high tack, cold temperature adhesive.

- Features superior tack and adhesion to recycled and corrugated cardboard, for which it was developed. Exhibits excellent performance at lower temperatures, e.g. labelling of chilled and frozen products.

Initial tack	High
Ultimate adhesion	High
Minimum application temperature	-10°C
Service temperature	-40°C to 70°C
Indirect Food	✓
Application	Substrates
✓ Freezer	✓ Cardboard
✓ Chilled	✓ Glass
✓ Wet Surfaces	✓ PET
Tight mandrel	✓ HDPE
Ice bucket	✓ LDPE
Durable	✓ PP
Removable	

C2076C

Rubber-based Hotmelt

A rubber based, high tack, chilling temperature adhesive.

- Suitable for use under general-purpose temperatures. Provides moisture resistance after application on a dry surface. Suitable for a wide variety of substrates including apolar, slightly rough and curved surfaces and recycled board.

Initial tack	High
Ultimate adhesion	Medium
Minimum application temperature	0°C
Service temperature	-40°C to 70°C
Indirect Food	✓
Application	Substrates
Freezer	✓ Cardboard
✓ Chilled	✓ Glass
✓ Wet Surfaces	✓ PET
Tight mandrel	✓ HDPE
Ice bucket	✓ LDPE
Durable	✓ PP
Removable	

S333

Emulsion Acrylic

An industrial general purpose durable acrylic based adhesive for filmic facestocks

- High degree of clarity and “wet out” for clear filmic facestocks
- Good initial tack and adhesion on a variety of substrates including apolar surfaces
- Exhibits low bleed characteristics
- Good die-cutting and stripping properties
- Offers a wide service temperature range include high temp durable performance
- Demonstrates good UV resistance
- Durable application adhesive

Initial tack	High
Ultimate adhesion	High
Minimum application temperature	-4°C
Service temperature	-40°C to 145°C
Indirect Food	
Application	Substrates
Freezer	Cardboard
Chilled	✓ Glass
Wet Surfaces	✓ PET
Tight mandrel	✓ HDPE
Ice bucket	LDPE
✓ Durable	✓ PP
Removable	



Adhesive / Special Purpose (continued)

Permanent (continued)

S369

Emulsion Acrylic

An excellent, general purpose industrial grade clear adhesive

- Good initial tack and adhesion on wide variety of substrates
- Exhibit low bleed characteristics
- Excellent die-cutting and stripping properties
- Durable application adhesive

Initial tack	Medium
Ultimate adhesion	High
Minimum application temperature	-4°C
Service temperature	-40°C to 145°C
Indirect Food	
Application	Substrates
Freezer	Cardboard
Chilled	✓ Glass
Wet Surfaces	✓ PET
Tight mandrel	✓ HDPE
Ice bucket	LDPE
✓ Durable	✓ PP
Removable	

S8020

Emulsion Acrylic

A special purpose permanent, clear acrylic based adhesive

- Featuring excellent UV resistance and weatherability together with good adhesion performance, even on apolar substrates.
- Exhibits a balance of high cohesive strength and adhesion to low surface-energy substrates.
- Specifically designed to exhibit excellent wet-out characteristics, good yellowing resistance, and excellent clarity.

Initial tack	Medium
Ultimate adhesion	Medium
Minimum application temperature	5°C
Service temperature	-20°C to 80°C
Indirect Food	✓
Application	Substrates
Freezer	Cardboard
Chilled	Glass
Wet Surfaces	✓ PET
Tight mandrel	✓ HDPE
Ice bucket	LDPE
✓ Durable	✓ PP
Removable	

S2060

Rubber-based Hotmelt

An excellent, high performance industrial grade adhesive

- Suitable for use in a wide range of durable labeling application which do not need extremely high temperature resistance.
- Featuring good initial tack and ultimate bond strength to a wide range of substrates.

Initial tack	High
Ultimate adhesion	Very High
Minimum application temperature	0°C
Service temperature	-40°C to 70°C
Indirect Food	✓
Application	Substrates
Freezer	✓ Cardboard
Chilled	✓ Glass
Wet Surfaces	✓ PET
Tight mandrel	✓ HDPE
Ice bucket	LDPE
✓ Durable	✓ PP
Removable	



Adhesive / Special Purpose (continued)

Permanent (continued)

S2059

Rubber-based Hotmelt

A specialty permanent rubber based adhesive suitable for demanding applications

- Specially designed to meet the demands of rough and textured surfaces
- Limited conversion speeds
- The construction will have a tendency to bleed, so therefore avoid tight rewinding
- Temperature levels of 50 degree celsius should not be exceeded
- Excessive exposure to sunlight may also result in degradation of the adhesive

Initial tack	Very High
Ultimate adhesion	Very High
Minimum application temperature	5°C
Service temperature	-40°C to 70°C
Indirect Food	✓
Application	Substrates
Freezer	✓ Cardboard
Chilled	✓ Glass
Wet Surfaces	✓ PET
✓ Tight mandrel	✓ HDPE
Ice bucket	✓ LDPE
Durable	✓ PP
Removable	

TS79

Rubber-based Hotmelt

A special purpose permanent, rubber based adhesive designed for demanding applications

- Specially designed to meet the demands of rough and textured surfaces, such as those in the tyre and textile industries
- Limited conversion speeds
- The construction will have a tendency to bleed, avoid tight rewinding
- Temperature levels of 70° Celsius should not be exceeded
- Excessive exposure to sunlight may result in the degradation of the adhesive

Initial tack	Very High
Ultimate adhesion	Very High
Minimum application temperature	0°C
Service temperature	-40°C to 70°C
Indirect Food	✓
Application	Substrates
Freezer	✓ Cardboard
Chilled	Glass
Wet Surfaces	✓ PET
Tight mandrel	✓ HDPE
Ice bucket	✓ LDPE
✓ Durable	✓ PP
Removable	

WLP

Emulsion Acrylic

A special purpose permanent acrylic emulsion adhesive designed for the wine market

- General purpose wine adhesive exhibiting excellent adhesive performance
- Offers good ice bucket performance when used with appropriate varnished facestocks
- Effective during extended storage in refrigeration
- Good die-cutting and stripping properties
- Exhibits low bleed characteristics
- Adhesive performance will be reduced if heavy embossing or foiling is applied - prior testing is strongly recommended.
- Labels must have a 3mm grain free zone measured from label edges.

Initial tack	High
Ultimate adhesion	High
Minimum application temperature	5°C
Service temperature	-20 °C to 70°C
Indirect Food	✓
Application	Substrates
Freezer	Cardboard
✓ Chilled	✓ Glass
Wet Surfaces	✓ PET
Tight mandrel	✓ HDPE
✓ Ice bucket	LDPE
Durable	✓ PP
Removable	



Adhesive / Special Purpose (continued)

Permanent (continued)

WLK202

Emulsion Acrylic

A special purpose extra permanent acrylic based adhesive designed specifically for demanding wine label applications

- Special purpose aggressive wine adhesive exhibiting excellent adhesive performance
- For use in difficult applications where moderate levels of moisture are present eg. sparkling wine
- Offers good ice bucket performance when used with appropriate varnished facestocks
- Effective during extended storage in refrigeration
- Suitable for neck labelling applications when matched with low memory facestocks
- Adhesive performance will be reduced if heavy embossing or foiling is applied - prior testing is strongly recommended.
- Labels must have a 3mm grain free zone measured from label edges.
- Where high levels of moisture are present it is recommended in-line air blowers are used prior to application
- The construction will have a tendency to bleed, so therefore avoid tight rewinding

Initial tack	Very High
Ultimate adhesion	Very High
Minimum application temperature	-5°C
Service temperature	-30°C to 70°C
Indirect Food	✓
Application	Substrates
Freezer	✓ Cardboard
✓ Chilled	✓ Glass
✓ Wet Surfaces	✓ PET
✓ Tight mandrel	✓ HDPE
✓ Ice bucket	✓ LDPE
Durable	✓ PP
Removable	

S2030

Emulsion Acrylic

A special purpose permanent acrylic emulsion adhesive designed for the wine market

- General purpose wine adhesive exhibiting excellent adhesive performance
- The product is designed for use in the beverage industry, especially for the labelling of wine bottles when the advantages of front & back body labels and neck / shoulder labelling on the same adhesive is important
- Adhesive performance will be reduced if heavy embossing or foiling is applied - prior testing is strongly recommended.
- Labels must have a 3mm grain free zone measured from label edges.

Initial tack	Very High
Ultimate adhesion	Very High
Minimum application temperature	5°C
Service temperature	-20°C to 80°C
Indirect Food	✓
Application	Substrates
Freezer	Cardboard
✓ Chilled	✓ Glass
Wet Surfaces	✓ PET
Tight mandrel	HDPE
✓ Ice bucket	LDPE
Durable	PP
Removable	



Adhesive / Special Purpose (continued)

Permanent (continued)

Z3338N

Emulsion Acrylic

A special purpose extra permanent acrylic based adhesive designed specifically for heavy condensated applications such as sparkling wines and champagnes

- Special purpose wine adhesive engineered to perform on cold/condensated glass surfaces
- For use in difficult applications where high levels of moisture are present eg. sparkling wine & champagne
- Offers good ice bucket performance when used with appropriate varnished facestocks
- Effective during extended storage in refrigeration
- Withstands variable temperature and humid environments
- Consistent label positioning on bottle surfaces with condensation

Initial tack	High
Ultimate adhesion	High
Minimum application temperature	-20°C
Service temperature	-50°C to 80°C
Indirect Food	✓
Application	Substrates
Freezer	✓ Cardboard
✓ Chilled	✓ Glass
✓ Wet Surfaces	✓ PET
✓ Tight mandrel	✓ HDPE
✓ Ice bucket	✓ LDPE
Durable	✓ PP
Removable	

S477A

Emulsion Acrylic

S477A is a permanent, emulsion acrylic adhesive featuring high initial tack.

- S477A features very good initial tack and adhesion properties on a wide range of substrates, including low surface energy substrates like HDPE or PP.

Initial tack	High
Ultimate adhesion	High
Minimum application temperature	5°C
Service temperature	-20°C to 80°C
Indirect Food	
Application	Substrates
Freezer	Cardboard
Chilled	✓ Glass
Wet Surfaces	✓ PET
Tight mandrel	✓ HDPE
Ice bucket	✓ LDPE
Durable	✓ PP
Removable	

Removable

Z3000

Rubber-based Hotmelt

Z3000 is a removable adhesive which meets the requirements of FDA 175.105 and FDA175.125B

- This adhesive is specially designed for adhesion to fresh fruits and vegetables with edible skin. This adhesive does not meet the requirements of FDA 21 CFR 175.125A for direct food contact.

Initial tack	High
Ultimate adhesion	Medium
Minimum application temperature	-4°C
Service temperature	-50°C to 70°C
Indirect Food	
Application	Substrates
Freezer	Cardboard
✓ Chilled	Glass
Wet Surfaces	PET
Tight mandrel	HDPE
Ice bucket	LDPE
Durable	PP
✓ Removable	



Liner





Liner contents

Glassine 57

- [BG33Wh FSC](#) 
- [BG40Wh FSC](#) 
- [BG50Wh FSC](#) 
- [BG33Bl FSC](#) 
- [BG40Bl FSC](#) 

PET 58

- [PET23](#)
- [PET30](#)

Kraft 59

- [CCK55](#)
- [rCCK80](#)
- [CCK130](#)
- [B90](#)
- [B100](#)



Liner / Glassine

BG33Wh FSC

A super calendered glassinated paper, available in white.

- The paper's translucent properties are perfectly suited to automatic label applicators and is particularly suitable for products in reels.

Basis Weight 50 g/m²

Thickness 48 µm

BG40Wh FSC

A super calendered glassinated paper, available in white.

- Designed for medium to high speed conversion. Good caliper consistency allows accurate kiss die cutting.
- The paper's translucent properties are perfectly suited to automatic label applicators and is particularly suitable for products in reels.

Basis Weight 57 g/m²

Thickness 51 µm

BG50Wh FSC

A super calendered glassinated paper, available in white.

- Designed for medium to high speed conversion. Good caliper consistency allows accurate kiss die cutting.
- The paper's translucent properties are perfectly suited to automatic label applicators and is particularly suitable for products in reels.

Basis Weight 78 g/m²

Thickness 69 µm

BG33Bl FSC

A super calendered glassinated paper, available in blue.

- The paper's translucent properties are perfectly suited to automatic label applicators and is particularly suitable for products in reels.

Basis Weight 50 g/m²

Thickness 43 µm

BG40Bl FSC

A super calendered glassinated paper, available in blue.

- Designed for medium to high speed conversion. Good caliper consistency allows accurate kiss die cutting.
- The paper's translucent properties are perfectly suited to automatic label applicators and is particularly suitable for products in reels.

Basis Weight 58 g/m²

Thickness 51 µm



Liner / PET

PET23

A clear polyester film giving optimum smoothness to the adhesive layer and featuring very high strength and toughness.

Basis Weight 33 g/m²

Thickness 23 µm

- For applications where highest clarity of the applied label is required i.e. the “no label look”. The films high strength and uniform caliper permit very high speed conversion and dispensing.
-

PET30

A clear polyester film giving optimum smoothness to the adhesive layer and featuring very high strength and toughness.

Basis Weight 43 g/m²

Thickness 30 µm

- For applications where highest clarity of the applied label is required i.e. the “no label look”. The films high strength and uniform caliper permit very high speed conversion and dispensing.
-



Liner / Kraft

CCK55

A one side clay coated kraft liner, available in white

- Features good dimensional stability. The Hygroflat liner suitable for high speed sheet fed laser printers and copiers.
- Suited for roll to sheet label conversion.

Basis Weight 55 g/m²

Thickness 58 µm

rCCK80

A one side clay coated kraft liner, available in white and consists of recycled content.

- Contains 5% recycled content, promote a more sustainable brand image and contribute to a circular economy.
- Features good dimensional stability, uniform thickness, toughness, and tear resistance which is required for good die-cutting in rotary and flat-bed.
- Exhibits good layflat property, which is necessary for sheets form applications, when paired with paper facestocks.
- Suited for roll to sheet label conversion

Basis Weight 80 g/m²

Thickness 80 µm

CCK130

A high strength clay-coated kraft paper.

- Features excellent dimensional stability, toughness, and tear resistance which is required for good die-cutting in rotary and flat-bed.
- Excellent layflat property, which is necessary for filmic sheets form applications
- Suited for roll to sheet label conversion

Basis Weight 130 g/m²

Thickness 130 µm

B90

A clay coated kraft liner, available in white.

- Featuring good dimensional stability and flatness during processing, combined with the resilience to support die cutting.
- Designed for excellent layflat needed in sheet products

Basis Weight 87 g/m²

Thickness 91 µm

B100

A clay coated kraft liner, available in white.

- Featuring good dimensional stability and flatness during processing, combined with resilience to support die cut.
- Designed for excellent layflat needed in sheet products
- Suitable for high quality process printing.

Basis Weight 100 g/m²

Thickness 87 µm



Product Selection Considerations

As part of our commitment to improve and innovate, these selection considerations were written to guide you through the product selection process.

Choosing the right product can be a challenge, but with Avery Dennison it's easy. Simply understand your requirements then call your local Avery Dennison representative.

1. Is the label to be permanent or removable?

- a) For removable labels ensure the substrate is strong enough to withstand label removal.
- b) Larger labels may require a stronger facestock to prevent tear on removal.
- c) A label is considered permanent if the bond to the substrate is substrate is impossible to remove without tearing the material.

2. What is the composition of the substrate?

- a) The composition of the substrate that the label will be applied to can have an effect on the ultimate strength of the bond that the label will form.
- b) On low surface energy materials, initial tack is the most important criteria. Adhesive levels will improve with longer dwell.

3. What is the texture of the substrate's surface?

- a) The texture of a substrate can have an impact on the formation adhesive.
- b) Textured materials do not allow 100% contact of the adhesive. Less contact means a smaller bonding area which will result in lower adhesion.
- c) Performance on heavily textured materials is improved with careful product selection.
- d) A more aggressive adhesive will maximize the adhesion at contact area.

4. What is the shape of the substrate?

- a) The shape of the substrate along with the size and stiffness of the label must be considered to ensure proper end-use performance. Curved surfaces (less than 25mm in diameter) will require an aggressive adhesive combined with a flexible facestock featuring little or no memory.
- b) Small labels or stiff facestocks may not adhere well on curved or irregular surfaces.

5. Is the application surface clean or contaminated?

- a) The cleanliness of the surface of the substrate when the label is applied will affect the ultimate adhesion of the label and the success of the application. Contamination from oil, grease, frost, dust, moisture and release agents are some causes of label failure.
- b) If contamination cannot be avoided, careful product selection can overcome the negative impact.



6. Are there any plasticisers present in the substrate?

- a) Plastics containing plasticisers (softeners) will degrade the adhesive bond strength and may render the label useless. Careful product selection can overcome the negative impact.

7. Are there any special application or exposure conditions that the label must withstand?

- a) Will the label be exposed to solvent/cleaning agents, large amounts of humidity or moisture, UV light or ozone?
- b) What is the application temperature of the label?
- c) Service Temperature - will the label be exposed to deep freeze conditions?

8. What are the printing, imprinting and conversion requirements?

- a) Most paper facestocks are suitable for all printing methods. Non-absorbent film facestocks require different considerations.
- b) When high quality process printing is required, careful selection of the facestock will be required.
- c) When imprinting is required, good resolution and smudge resistance is important.
- d) Corona treated films - effectiveness of the corona treatment reduces in time and can also be affected by abrasion or damage. To ensure optimum wettability and ink bond, additional in-line corona treatment is recommended for optimum ink key.
- e) All dies should be proofed to the construction.
- f) Complex shaped labels and square corners may limit the conversion speed.



Avery Dennison
Label and Packaging Materials

Thailand
110/1 Moo 1 Tumbol Srisajorakhe Yai
Amphur Bangsaothong
Samutprakarn 10570
Thailand

Malaysia
No. 37 & 38, Jalan P4/6 Section 4,
Bandar Teknologi Kajang,
43500 Semenyih Selangor
Malaysia

Indonesia
Kawasan Industri Jababeka
Tahap 7 Blok B No 5,
Desa Wangunharja, Kecamatan Cikarang Utara,
Kabupaten Bekasi 17550 - Indonesia

Vietnam
Lot 7-2, Road M7, Tan Binh IP
Binh Hung Hoa Ward, Binh Tan District
Ho Chi Minh City, Vietnam

Singapore
5B, Toh Guan Road East, #05-03, 608829
Singapore

Philippines
Unit 2925
L29 Joy Nostalg Center 17 ADB Avenue
Ortigas Center
Pasig Center 1600 Philippines